

SILIKAL® HK 21 coving paste

Reactive methacrylate coving paste



Expect more from your floor.

SILIKAL® HK 21 coving paste is a formulated ready-to-use methacrylic-based paste for the easy manufacture of covings.

Application

SILIKAL® HK 21 coving paste is outstandingly suitable for the manufacture of indoor covings in both dry and wet areas when applied with SILIKAL® Filler FM, FS or SILIKAL® Filler QS 0.7 – 1.2 mm. The hardening time of the almost non-yellowing coving paste is about 40 minutes at +20 °C. It can be used at temperatures ranging from 0 °C to +35 °C, enabling application to progress rapidly. For coating thickness of more than 10 mm, a first half thick cove must be installed for curing as to avoid any overheating. The final coving to follow as soon as the first layer has cooled down. For covings thicker than 20 mm and for all outdoor covings SILIKAL® R17-thix mortar must be used.

Advice on application

The mixing ratio is 15 kg of SILIKAL® Filler FM, FS or SILIKAL® Filler QS 0.7 – 1.2 mm and 5 kg of SILIKAL® HK 21 coving paste. The quantity of filler can be varied from 12 – 18 kg according to the material and ambient temperature in order to ensure individual application or stability.

This batch is sufficient for approx. 8 – 10 m of coving at a height of 10 cm.

Under no circumstances should other untested additives be added to the mixture.

Mixing the coving paste

The corresponding quantity of SILIKAL® Filler FM, FS or SILIKAL® Filler QS 0.7 – 1.2 mm as well as SILIKAL® Hardening Powder is added to the SILIKAL® HK 21 coving paste as indicated in the “**Hardener dosages**” table, all mixed together intensively for about one minute using a high-speed propeller agitator. You must remember that the hardening powder has to be mixed in with the coving paste first before the filler is added.

The pot life at normal temperatures is about 15 minutes, the hardening time about 40 minutes. The values indicated will vary according to the ambient temperature.

Guideline recipe and batch quantities

Item	Component	Guideline recipe (% by weight)	Comments	Batch for 10 litre bucket	
1	SILIKAL® HK 21 coving paste	25 %		3 kg	3 litres
2	SILIKAL® Filler FS, FM or QS	75 %		9 kg	approx. 6 litres
	Total:	100 %	Average consumption: 1.85 kg per litre Coving volume	12 kg	approx. 6.5 litres
3	SILIKAL® Hardening Powder	1.0 – 3.5 % related to item 1	See “Hardener dosages” table for quantities	30 – 105 g	

Characteristics of HK 21 as delivered

Property	Measuring method	Approx. value
Viscosity at +20 °C		Pasty
Flow time at +20 °C, ISO 4 cup	DIN 53 244	N/A
Density D ₄ ²⁰	DIN 51 757	1.02 g/cm ³
Flash point	DIN 51 755	+10 °C
Pot life at +20 °C (1.5 % pbw. hardening powder)		approx. 15 min.
Application temperature		0 °C to +35 °C

Silikal

✉ Ostring 23
☎ +49 (0) 61 82 / 92 35-0
🌐 www.silikal.de

63533 Mainhausen, Germany
☎ +49 (0) 61 82 / 92 35-40
@ mail@silikal.de

Silikal product information

Issue MMA 4.02.A

January 2020

Data sheet SILIKAL® HK 21

Page 1 of 2

Characteristics of HK 21 in the hardened state (1 : 3 filled)

Property	Measuring method	Approx. value
Density	DIN 53 479	1.85 g/cm ³
Compressive strength	DIN 1164	40.0 N/mm ²
Tensile strength in bending	DIN 1164	17.0 N/mm ²
Modulus of elasticity	DIN 53 457	2100 N/mm ²
Water absorption, 4 days	DIN 53 495	125 mg/(50 · 50 · 4 mm)
Water vapour permeability	DIN 53 122	1.05 · 10 ⁻¹¹ g/cm · h · Pa

Hardener dosages

Temperature	Hardening powder % pbw. *	Pot life approx. min.	Hardening time approx. min.
0 °C	3.5	20	60
+10 °C	2.5	17	45
+20 °C	1.5	15	40
+30 °C	1.0	12	30

* The quantity of hardening powder is always related to the quantity of resin.

👁 For further information, please refer to the separate product information sheet "SILIKAL® Hardening Powder".



Other applicable documents Data sheet

SILIKAL® Hardening Powder	SILIKAL® Hardening Powder
General processing information	AVH
The substrate	DUG
Fillers and pigments	FUP
Information on safety and protection	SUS
Storage and transport	LUT

Silikal product information

Issue MMA 4.02.A

January 2020

Data sheet SILIKAL® HK 21

Page 2 of 2

Silikal

✉ Ostring 23
☎ +49 (0) 61 82 / 92 35-0
🌐 www.silikal.de

63533 Mainhausen, Germany
☎ +49 (0) 61 82 / 92 35-40
@ mail@silikal.de